

FLUID COMPATIBILITY TABLE

These are general guidelines only and users must conduct their own functional tests to determine the suitability of any compound for their particular application.

R = Recommended
M = Marginal
U = Unsatisfactory
X = Insufficient Data

Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer	Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer
Acetaldehyde	U	U	R	U	U	U	R	U	Bromine	U	U	U	U	U	U	U	R
Acetamide	R	U	R	R	U	U	M	U	Bromobenzene	U	U	U	U	U	U	U	R
Acetic Acid	M	M	R	R	U	U	R	U	Bunker Oil	R	U	U	U	R	R	U	R
Acetone	U	M	R	M	U	U	M	U	Butane	R	M	U	R	R	U	U	R
Acetophenone	U	U	R	U	U	U	U	U	Butter	R	U	M	R	R	R	R	R
Acetylene	R	R	R	R	X	X	R	R	Butyl Acetate	U	U	U	U	U	U	U	U
Ammonia	R	R	R	R	U	X	R	R	Butyl Alcohol	R	R	R	R	U	U	U	U
Ammonium Hydroxide	R	R	R	R	U	U	R	R	Butyl Amine	M	U	U	U	U	U	R	U
Amyl Acetate	R	U	M	U	U	U	U	U	Butyl Carbitol	U	U	R	M	U	X	U	M
Anderol L-774	M	U	U	U	R	U	U	R	Butyl Cellosolve	M	U	R	M	U	U	U	U
Antifreeze	R	R	R	R	U	U	R	R	Butyraldehyde	U	U	R	U	U	U	U	U
Aniline	U	U	R	U	U	U	U	M	Carbitol	R	R	R	R	U	U	U	R
Ansul Ether	M	U	M	U	U	R	U	U	Carbitol Acetate	U	U	U	U	U	U	U	R
Aroclors	M	U	U	U	U	X	M	R	Carbon Disulfide	U	U	U	U	U	X	U	R
Askarel	R	U	U	U	U	U	U	R	Carbon Tetrachloride	R	U	U	U	U	U	U	R
ASTM #1	R	U	U	R	R	R	R	R	Carbonic Acid	R	R	R	R	R	R	R	R
ASTM #3	R	U	U	U	R	R	U	R	Castor Oil	R	R	R	R	R	R	R	R
ASTM Fuel A	R	U	U	R	R	R	U	R	Cellosolve	U	R	U	U	U	U	U	U
ASTM Fuel B	R	U	U	U	U	R	U	R	Chassis Grease	R	U	U	M	R	X	U	R
ASTM Fuel C	R	U	U	U	U	R	U	R	Chloracetic Acid	U	U	R	U	U	X	U	U
ASTM Fuel D	M	U	U	U	U	R	U	R	Chloracetone	U	U	R	U	X	X	U	U
Auto. Transmission Fluid	R	U	U	M	R	R	M	R	Chlordane	R	U	U	M	X	X	U	R
Beer	R	R	R	R	U	U	R	R	Chlorine	U	U	R	U	U	U	X	R
Benzaldehyde	U	U	U	U	U	U	U	U	Chlorobenzol	U	U	U	U	U	U	U	R
Benzene	U	U	U	U	U	U	U	U	Chloroform	U	U	U	U	U	U	U	R
Benzine	R	U	U	R	R	R	U	R	Chlorsulfonic Acid	U	U	U	U	U	U	U	U
Benzoic Acid	U	U	U	X	U	U	U	R	Chrome Plating Solution	U	U	R	U	U	U	U	R
Benzophenone	U	U	R	R	U	U	U	R	Chromic Acid	U	U	X	U	X	X	M	R
Benzyl Alcohol	U	U	U	R	U	U	X	R	Citric Acid	R	R	R	R	X	X	R	R
Bleach	R	R	R	R	U	U	U	R	Cod Liver Oil	R	U	U	R	R	U	U	R
Borax	R	R	R	U	R	R	R	R	Coffee	R	U	R	U	U	U	U	R
Boric Acid	R	R	R	R	U	R	R	R	Corn Oil	R	U	U	U	R	U	U	R
• Brake Fluid (non-Petroleum)	U	R	R	M	U	U	M	U	Creosote	R	U	U	R	R	M	U	R
									Creoste Oil	R	U	U	M	X	X	M	R

• Requires special formulation of EPDM.

FLUID COMPATIBILITY TABLE

These are general guidelines only and users must conduct their own functional tests to determine the suitability of any compound for their particular application.

R = Recommended
M = Marginal
U = Unsatisfactory
X = Insufficient Data

Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer	Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer
Creosylic Acid	U	U	U	U	U	U	U	R	Formic Acid	M	R	R	R	X	X	M	U
Crude Oil	R	U	U	U	R	X	U	R	Freon 12	R	R	R	R	X	R	U	R
Cyclohexane	R	U	U	M	R	R	U	R	Fuel Oil	R	U	U	R	R	U	U	R
Cyclohexanol	R	U	U	R	X	X	U	R	Furan	U	U	X	U	U	X	X	R
Decalin	U	U	U	U	U	U	U	R	Furfural	U	U	R	U	U	U	U	R
Denatured Alcohol	R	U	R	R	U	U	R	R	Fufuryl Alcohol	U	U	R	U	U	U	U	X
Diacetone	U	U	U	U	U	U	U	R	Fyrquel	U	U	R	U	U	U	U	R
Dibutyl Amine	U	U	U	M	U	U	U	U	Gallic Acid	R	R	R	R	U	U	X	R
Dibutyl Phthalate	U	U	R	U	U	X	X	M	Gasoline	R	R	U	R	R	R	U	R
Dichloro Aniline	U	U	U	U	U	U	U	M	Gelatin	R	R	R	R	R	U	R	R
Dichloro Butane	R	U	U	U	U	U	U	R	Glucose	R	R	R	R	X	U	R	R
Diesel Oil	R	U	U	M	U	U	U	R	Glycerine	R	R	R	R	U	U	R	R
Diethylamine	R	R	R	R	U	M	R	U	Heptane	R	U	U	R	R	R	U	R
Diethyl Benzene	M	U	U	U	X	X	X	R	Hexaldehyde	R	U	U	R	X	X	R	R
Diethylene Glycol	R	R	R	R	U	U	R	R	Hexane	R	U	U	R	R	R	U	R
Dimethyl Ether	U	U	U	M	M	U	U	U	Hexanol	R	U	M	R	R	R	U	R
Dimethyl Formamide	U	X	R	X	X	X	R	U	Home Heating Oil	R	U	U	M	R	R	R	R
Dimethyl Phthalate	U	U	R	U	U	X	X	R	Hydrazine	R	R	R	R	X	X	R	X
Dimethyl Terephthalate	U	U	U	U	U	U	U	R	Hydrochloric Acid	R	R	R	R	M	U	M	R
Dioctyl Phthalate	U	U	R	U	U	U	M	R	Hydrocyanic Acid	R	R	R	R	U	X	U	R
Dioxane	U	U	R	U	U	U	U	R	Hydrogen Peroxide	R	R	R	R	U	X	R	R
Diphenyl	U	U	U	U	U	U	U	R	Hydrogen Sulfide	U	U	R	R	U	X	M	U
Dow Corning 550	R	R	R	R	R	R	R	R	Hydroquinone	M	U	U	U	U	X	X	R
Dow Gard	R	R	R	R	M	M	R	R	Hypoid Gear Lube	R	U	U	U	R	X	M	R
Dowtherm A & E	U	U	U	U	U	U	U	R	Iodine	R	R	R	R	X	X	X	R
Elco 28	R	U	U	M	R	R	R	R	Isocyanate	X	X	X	X	X	X	X	R
Epoxy Resins	X	X	R	R	X	X	X	U	Iso Octane	R	U	U	R	R	R	U	R
Ethane	R	U	U	R	R	M	U	R	Iso Phorone	U	U	R	U	U	U	U	U
Ethanol	R	R	R	R	U	R	R	R	Isopar	R	X	U	R	R	R	U	R
Ethanolamine	R	R	R	R	U	M	R	U	Isopropanol	R	R	R	R	U	U	U	R
Ethyl Acetate	U	U	R	U	U	U	R	U	Isopropyl Acetate	U	U	R	U	U	U	U	R
Ethyl Benzene	U	U	U	U	U	U	U	R	JP-4(MIL-J-5624)	R	U	U	U	R	R	U	R
Ethyl Cellulose	R	R	R	R	U	R	R	U	JP-4(MIL-J-5624)	R	U	U	U	R	R	U	R
Ethyl Chloride	R	R	R	R	M	R	U	R	Kerosene	R	U	U	U	R	R	U	R
Ethyl Ether	M	U	M	U	U	R	U	U	Lactic Acid	R	U	R	R	U	U	X	R
Ethyl Formate	U	U	R	R	X	X	X	R	Lacquers	U	U	U	U	U	U	U	U
Ethyl Hexanol	M	R	R	R	X	X	X	R	Lard	R	U	R	R	R	U	R	R
Ethyl Merlaptan	U	U	X	M	X	X	M	R	Linoleic Acid	R	U	U	R	X	X	R	R
Ethylene Chloride	U	U	U	U	U	U	U	R	Linseed Oil	R	U	M	M	R	X	R	R
Ethylene Oxide	U	U	R	U	U	U	U	U	Lye Solutions	R	U	R	R	U	U	U	R
Formaldehyde	M	M	R	M	U	U	R	U	Malathion	U	U	U	X	X	X	U	R
									Maleic Acid	U	U	U	U	U	X	X	R

FLUID COMPATIBILITY TABLE

These are general guidelines only and users must conduct their own functional tests to determine the suitability of any compound for their particular application.

R = Recommended
M = Marginal
U = Unsatisfactory
X = Insufficient Data

Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer	Fluid	Nitrile	SBR	EPDM	Neoprene	Polyacrylate	Urethane	Silicone	Fluoroelastomer
Mercury	R	R	R	R	X	X	X	R	Propyl Acetate	U	U	R	U	U	U	U	U
Meter-Cresol	U	U	U	R	R	U	U	R	Pydraul	U	U	R	U	U	U	U	R
Methane	R	U	U	R	R	M	U	R	Pyranol	R	U	U	R	R	R	U	R
Methanol	R	R	R	R	U	U	U	U	Pyridine	U	R	U	U	U	X	U	U
Methyl Acetate	U	U	R	R	U	U	U	U	Rapeseed Oil	R	U	R	R	R	R	U	R
Methacrylic Acid	U	U	R	R	U	U	U	M	Resurcinol	X	R	R	X	X	X	X	X
Methyl Cellosolve	M	U	R	R	U	U	U	M	SAE 10W30	R	U	U	M	R	R	R	R
Methylene Chloride	U	U	U	U	U	U	U	U	Seawater	R	R	R	R	U	U	R	R
Methyl Ethyl Ketone	U	U	R	U	U	U	U	U	Silicone Grease	R	R	R	R	R	R	R	R
Methyl Mercaptan	X	X	R	X	X	X	X	X	Silver Nitrate	R	R	R	R	R	R	R	R
Milk	R	R	R	R	U	U	R	R	Skelly Solvent	R	U	U	U	X	X	X	U
Mineral Oil	R	U	M	R	R	R	R	R	Skydrol	U	U	R	U	U	U	U	U
Mineral Spirits	R	U	U	U	R	R	U	R	Skydrol 500	U	U	R	U	U	U	U	U
Monovinyl Acetylene	R	R	R	R	X	X	R	R	Sodium Hydroxide	R	R	R	R	U	U	U	R
Mustard	X	R	R	X	X	X	R	R	Sovasol	R	U	U	R	R	R	U	R
Naphtha	R	U	U	U	R	R	U	R	Soy Bean Oil	R	U	M	M	R	X	R	R
Naphthalene	U	U	U	U	X	X	U	R	Stearic Acid	R	R	R	R	R	U	U	R
Naphthenic Acid	R	U	U	U	X	X	U	R	Stoddard Solvent	R	U	U	R	R	R	U	R
Natural Gas	R	R	U	R	R	R	R	R	Sucrose	R	R	R	R	U	U	U	R
Neatsfoot Oil	R	U	R	U	R	R	R	R	Sulfuric Acid	R	R	R	R	R	U	U	R
Nitric Acid	U	M	R	U	U	U	U	M	Tall Oil	R	U	U	M	R	U	X	R
Nitrobenzene	U	U	U	U	U	U	U	R	Tannic Acid	R	R	R	R	U	X	R	R
Nitropropane	U	U	R	U	U	U	U	U	Tar	R	U	U	M	U	X	R	R
Octane	R	U	U	U	U	U	U	R	Tartaric Acid	R	R	R	R	X	X	R	R
Octanol	R	R	R	R	U	U	R	R	Tetrachloro Ethane	U	U	U	U	U	U	U	R
Oleic Acid	M	U	U	M	X	X	U	R	Tetralin	U	U	U	U	U	U	U	R
Oleum	R	U	U	M	X	X	U	R	Tidewater Oil	R	U	U	U	R	R	R	R
Oronite 8200	R	U	U	R	X	R	U	R	Toluene	U	U	U	U	U	U	U	R
Oxalic Acid	R	R	R	R	R	X	X	R	Trichloro Ethylene	M	U	U	U	U	U	U	R
Peanut Oil	R	U	M	M	R	X	R	R	Triethanol Amine	M	R	R	R	U	U	X	U
Pentane	R	M	U	R	R	U	U	R	Turbine Oil	R	U	U	U	R	R	U	R
Perchlorethylene	R	U	U	U	U	U	U	R	Turpentine	R	U	U	U	R	U	U	R
Petroleum Ether	R	U	U	U	U	U	U	R	UCDN 50HB280X	R	R	R	R	X	X	R	R
Phenol	U	U	U	U	U	U	U	R	Univis J-43	R	U	U	R	R	R	U	R
Phenylhydrazine	U	M	U	U	U	X	X	R	Varnish	R	U	U	U	U	M	U	R
Phosphoric Acid	R	R	R	R	M	U	R	R	Vinegar	R	R	R	R	U	U	R	R
Pine Oil	R	U	U	U	U	X	X	R	Water	R	R	R	R	U	U	R	R
Potassium Hydroxide	R	R	R	R	U	U	M	U	Wheat Germ Oil	R	U	U	M	R	R	R	R
Propane	R	U	U	R	R	M	U	R	Whiskey & Wine	R	R	R	R	U	U	U	R
Propanol	R	R	R	R	U	U	R	R	Wood Oil	R	U	U	R	X	M	U	R